

[Code of Federal Regulations]
[Title 21, Volume 3]
[Revised as of April 1, 2008]
[CITE: 21CFR177.1460]

TITLE 21--FOOD AND DRUGS
CHAPTER I--FOOD AND DRUG ADMINISTRATION
DEPARTMENT OF HEALTH AND HUMAN SERVICES
SUBCHAPTER B--FOOD FOR HUMAN CONSUMPTION (CONTINUED)

PART 177 -- INDIRECT FOOD ADDITIVES: POLYMERS

Subpart B--Substances for Use as Basic Components of Single and Repeated Use Food Contact Surfaces

Sec. 177.1460 Melamine-formaldehyde resins in molded articles.

Melamine-formaldehyde resins may be safely used as the food-contact surface of molded articles intended for use in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting, or holding food in accordance with the following prescribed conditions:

(a) For the purpose of this section, melamine-formaldehyde resins are those produced when 1 mole of melamine is made to react with not more than 3 moles of formaldehyde in water solution.

(b) The resins may be mixed with refined woodpulp and the mixture may contain other optional adjuvant substances which may include the following:

| List of substances | Limitations |
|--|--|
| Colorants used in accordance with 178.3297 of this chapter | |
| Diocetyl phthalate | For use as lubricant. |
| Hexamethylenetetramine | For use only as polymerization reaction control agent. |
| Phthalic acid anhydride | Do. |
| Zinc stearate | For use as lubricant. |

(c) The molded melamine-formaldehyde articles in the finished form in which they are to contact food, when extracted with the solvent or solvents characterizing the type of food and under the conditions of time and temperature as determined from tables 1 and 2 of 175.300(d) of this chapter, shall yield net chloroform-soluble extractives not to exceed 0.5 milligram per square inch of food-contact surface.
[42 FR 14572, Mar. 15, 1977, as amended at 56 FR 42933, Aug. 30, 1991]